

Acrylic surfaces repair

MINOR acrylic surface repair

Oceania Baths suggests the following instructions for the repair of minor scratches or blemishes on acrylic surfaces. This basic procedure may be used as long as the scratch or blemish has not penetrated the acrylic surface to reach the fibreglass laminated coating underneath.

Please note that steps 1 and/or 2 may be skipped depending on the magnitude of the scratch or blemish to be repaired.

- Lightly wet sand the damaged area with a #600 grit wet/dry sandpaper (if required);
- With a damp cloth, apply an automotive rubbing compound to rub out and reduce the scratch or scuff;
- With a soft cloth, use a fine rubbing compound and polish out the light scratches;
- With a soft cloth, use a polishing paste or glaze to clean and finish the repaired area.

MAJOR acrylic surface repair

In the event of a deep scratch or blemish, where the fibreglass laminated sub-surface has been penetrated, Oceania Baths shall be contacted in order to recommend an acrylic repair professional.

Never try to repair a deep scuff or blemish without proper instructions.

For the acrylic repair professional nearest you, please contact our Oceania Baths customer Service Department

Technical service:

Email: support@oceaniabaths.com

Tel: 1-877-332-4224